

## Lithofin TC Sealant

### Description

A special product from the LITHOFIN program for terracotta and terracotta (method 1 -modern-). Ready-to-use, solvent-free product with natural waxes and high-quality additives.

### Features

Lithofin TC Sealant forms a self-shining and protective film. This causes impurities to remain on the surface and cannot penetrate. Maintenance is made much easier, as the surface roughness is reduced at the same time. The appearance of the surface is improved, but retains its natural colour structure. The film is very abrasion-resistant, UV-resistant and non-yellowing. Lithofin TC Sealant is easy and safe to work with.

#### Technical data:

Density: approx. 1.0 g/cm<sup>3</sup>  
pH value: approx. 9 (concentrate),  
Flash point: approx. 85°C (c.C.)  
Appearance: Thin, white, milky  
Odour: almost odourless  
Solubility in water: good, complete

### Scope of application

For the self-shining finish of coverings made of terracotta, terracotta, clay slabs, terres cuites, etc. indoors. Also suitable for factory-treated or waxed terracotta panels.

Note: Salt glazed surfaces should only be treated thinly with Lithofin TC Sealant.

The pre-impregnation of untreated, absorbent cotto panels with Lithofin Impregnator improves the protective effect and makes the surface appear lighter.

### Processing

Apply Lithofin TC Sealant to the clean and dried covering with a Lithofin applicator, sponge or lambskin mop generously and evenly. Lithofin TC Sealant can also be sprayed on with a garden sprayer and spread immediately with a sponge. After a drying time of approx. 40 to 60 minutes, a second application must be made. Avoid puddles and dripping or wipe over immediately with product solution. For highly absorbent substrates, a third application may be required. Apply a little more thinly to all pre-treated or waxed surfaces. Cleaning the tools with water.

Processing temperature: 5 to 25°C.

Please note: Do not walk on the topping during the drying phase. Always treat the entire surface of a room. Wipe off splashes on wood, glass, varnish, etc. with a damp cloth.

Coverage: approx. 5 to 10 m<sup>2</sup>/litre for soft clay slabs, terres cuites, Spanish and French terracotta species (applied 2 times); approx. 10 to 15 m<sup>2</sup>/litre for Florentine and Italian. Cotto (2 applications); approx. 10 to 15 m<sup>2</sup>/litre for pre-impregnated, pre-treated or waxed surfaces.

### Aftercare

If the protective effect decreases, Lithofin TC Sealant can also be added to the mopping water if necessary (approx. 1 cup / 10 litres of water)

### Storage

Sealed, cool and frost-free. Not above 25°C; can be stored for up to 3 years.

### Environmental protection

Free of organic solvents, water-based.

Disposal: The container is made of environmentally friendly polyethylene (PE) and is recyclable. Rinsed containers can be disposed of and recycled via the recyclable material collection system (see note on label).

For information on labelling, transport and disposal, please refer to the safety data sheet.

### Packaging units (PU)

- a) 1 litre bottle with child-resistant cap  
(10 pcs. in a box)
- b) 5 liter canister (2 pieces in a box)

Please note that the environmental and safety information applies to the (concentrated) product in delivery form. If dilution is appropriate for the application, the classification may change.  
This information can and should only provide non-binding advice.  
The use of the products must be adapted to the local conditions and the surfaces to be treated. If there is no experience and in all cases of doubt, the product should be tried out in an inconspicuous place beforehand.  
(EN11.25/9.25)